

TYTAN EURO-LINE Sanitary Silicone

Sealant with an acid curing system, containing agents preventing the formation and growth of mold, fungi and algae. After hardening, it creates a non-shrink and flexible joint. It is characterized by excellent adhesion to glass, ceramics, porcelain and wood. Especially recommended for use in kitchens, bathrooms and rooms with high humidity.



BENEFITS

- excellent resistance to mould and fungus
- good adhesion to many smooth building materials

RECOMMENDED USES

- sealing glass in display cabinets, marks, cable ducts
- protection of polyurethane foams against UV radiation
- sealing baths, hand basins, showers, sinks and other sanitary facilities and other water supply equipment
- sealing of ceramic tiles
- small home repairs

NORMS / ATESTS / CERTIFICATES

The product meets requirements of:

- EN 15651-3:2012 S, S1

TECHNICAL DATA

Uncured - tested at 23°C and 50% relative humidity	Value
Density (ISO 2811-1) [g/ml]	0,91 - 0,93
Skin formation time [min]	5 - 45
Tack Free [min]	5 - 25
Curing rate [mm/24h]	1 - 2
Cured - tested after 4 weeks at 23°C and 50% relative humidity	Value
Module at 100% elongation (ISO 37) [MPa]	0,2 - 0,3
Elongation at break (ISO 37) [%]	500 - 800
Shore A hardness (ISO 868)	10 - 14
Temperature resistance [°C]	-40 - +100
Adhesion to surface	Value
Stainless steel	+/-
Ceramic tile	+
PS (polystyrene)	+/-
Glass	+
Raw wood (pine)	+
Hard PVC (polyvinyl chloride)	+
Colour	Value
White	RAL9003
Transparent	+
Black	RAL9005

Brown	+
Grey	+
Beige	+
Conditions of application	Value
Surface temperature [°C]	+5- +40
Container temperature [°C]	+0 - +25
Application temperature [°C]	+5 - +40

METHOD OF USE

Prior to application, read safety instruction presented in MSDS.

Surface preparation

- Bonding surfaces must be clean, dry (not frosted) free of dust, rust, old loose material, oil, grease, paint and other dirt which reduces the adhesion of the sealant.
- Surfaces best degrease with acetone or ethanol (glass, glaze, metal) or detergent (synthetic materials).
- To avoid dirtiness around the gap and to maintain equal line use adhesive tapes which should be removed immediately after finishing sealing.
- Sealant does not require using primer on most surfaces but on some specific surfaces may have to use it to improve adhesion.
- Joint width should be as to be able to carry movement in range calculated for sealant in question (movement accommodation).
- The sealant bead should not be wider than 25 mm and the minimum joint width should be 6 mm to allow in the construction field proper application and tooling of sealant. The ideal ratio of joint width : depth is 2 : 1.
- For proper design deep joints should be filled with back-up rod.
- In movable joints tripartite sealant adhesion to the surface should be avoided because it can cause its damage. For this purpose if depth of the slots does not allow introduction of polyurethane foam, use dilatation tape or back-up rod. Using foam or tape causes bipartite sealant adhesion and allows proper work with the joint.
- If joints are too shallow to allow backing material to be used, we recommend use of adhesive tape. This acts as a back-up rod to prevent seal in forming of three-sided adhesion.

Product preparation

- Prior to application, the product should be conditioned at room temperature.

Application

- Cut off the top of the threaded adapter. Screw the nozzle tip on and cut off at a 45° angle, with the diameter equal to the gap width.
- Cut off the top of the foil. Screw the nozzle tip on and cut off at a 45° angle, with the diameter equal to the gap width.
- Squeeze sealant by mechanical or pneumatic gun.
- Treatment make at the time of workability given in the technical data table.
- Applied sealant should be smoothed immediately with a spatula soaked in soapy water for best result.
- Remove masking tape before skin will form.
- Joint should be allowed to fully cure.

Works after completion of application

- Uncured product should be removed from hands, tools and dirty surfaces with paper towel.
- After curing, remove from hands with water and soap; from tools remove mechanically. or using agent for removing silicones - Silicone Remover.
- DO NOT WASH HANDS WITH SOLVENTS.

Remarks / restriction

- Do not apply on wet surfaces.
- Due to the acetic acid released during curing, acid silicone is not recommended for use on calcareous substrates such as concrete, plaster, brick.
- Sealant is not intended for sealing joints of natural stone, such as granite, sandstone, marble, etc.
- Sealant should not be used on bituminous surfaces, partially vulcanized rubber, chloroprene or other construction materials that bleed oils, plasticizers or solvents.
- Do not apply on sensitive metal surfaces for example copper and its alloys and silver steel of mirrors.
- Sealant is not recommended for joints that are permanently under water, because it can cause physical changes.
- Do not use in totally confined spaces where it is not exposed to atmospheric moisture, because the sealant requires atmospheric moisture for cure.
- Sealant is not intended for applications involving structural glazing.
- Silicone should not be painted.
- Not suitable for bonding aquariums and terrariums.
- It is not suitable for direct contact with food and medical uses. Sealant was not duly tested and it is not suitable for medical and pharmaceutical applications.
- Do not apply on PE, PP - no adhesion.
- Not suitable for bonding mirrors.

ADDITIONAL INFORMATION

All given parameters are based on laboratory tests compliant with internal manufacturer's standards and strongly depend on product hardening conditions (c.a., ambient, surface temperature, quality of used equipment and skills of person applying the product).

TRANSPORT / STORAGE

Warranted shelf life is 18 months from the manufacturing date when stored in unopened, original package at temperature from +0 °C to +25 °C in a dry place protected from freezing.

Product can be transported at low temperatures up to - 30 °C for up to 2 weeks, before using the product should be conditioned for 24 hours at +23 °C.

Precautions should be taken when the product after thawing out is frosted again - is resistant to 2 cycles of freezing/thawing out.

CATALOGUE DATA

Nominal capacity / volume / size	Colour	Number of pieces per collective package	Index	EAN Code
280 ml	transparent	12	10047683	5902120195602
280 ml	transparent	12	10040934	5902120168040
280 ml	transparent	12	10051313	5902120231669
280 ml	white	12	10047675	5902120195565
280 ml	white	12	10040939	5902120168064
280 ml	white	12	10051312	5902120231768
290 ml	transparent	12	10026223	5902120019816

SAFETY AND HEALTH PRECAUTIONS

For detailed information find Material Safety Data Sheet available at producer upon request.

All written or oral information, recommendations and instructions are given according to our best knowledge, tests and experience, in good faith and in compliance with manufacturer's principles. Each user of this material will make sure in every possible way, including verification of the final product in proper conditions, about suitability of the supplied materials for their intended purposes. The manufacturer is not liable for any losses incurred due to inaccurate or erroneous application of the manufacturer's materials.