

TYTAN PROFESSIONAL Lexy 20 Multiposition PU Foam 300 ml

10024873, 10021802, 10044878, 10045239, 10021798

Innovative all-season straw foam with the features of gun foam and very high performance. Available in a wide range of capacities. Modern recipe allows application in any position of the can. It has a precise applicator giving great comfort of work.



BENEFITS

- high foam yield
- decreased foam pressure
- decreased foam volume increase (postexpansion)
- increased foam multipositioning
- standard foam flammability
- normal foam adhesion to surface

RECOMMENDED USES

- sealing for window fitting
- sealing for door fitting
- filling free spaces, cracks, gaps, pipe penetrations
- sealing roof, wall and floor joints
- thermal insulation
- acoustic insulation

NORMS / ATESTS / CERTIFICATES

Additional information

- ITB-KOT-2018/0441

TECHNICAL DATA

Parameter (+23°C/50% RH)	Value
Full cure time (RB024) [h]	24
Cutting time (EN 17333-3:2020). The result given for a foam strip of 3 cm diameter [min]	≤40
Flammability class (DIN 4102)	B3
Flammability class (EN 13501-1:2008)	F
Dimensional stability (EN 17333-2:2020) [%]	≤5
Heat conductivity coefficient (λ) (RB24) [W/mK]	0,036
Secondary increase in volume (post-expansion) (EN 17333-2:2020) [%]	130 - 180
Capacity (free foaming) (RB024) [l]	18 - 20
Capacity in gap (The value given for a gap with dimensions 35*1000*35 (width *length *depth [mm])) (RB024) [l]	11 - 12
Skin formation time (EN 17333-3:2020) [min]	≤10
Certification M1	M1
Certification O2	O2
Acoustic insulation (EN ISO 10140-1:2010+A1:2012+A2:2014)	62
Compressive stress at 10% relative deformation [PN EN 826:2013] [kPa]	≥ 20
Tensile strength perpendicular for frontal surfaces [PN-EN 1607:2013-07] [kPa]	≥ 60
Compressive strength [PN-EN 1607:2013-07] [kPa]	≥ 35
Adhesion of foam applied at 0°C to the substrate wood [PN-EN 1607:2013] [kPa]	≥ 50

Adhesion of foam applied at 0°C to metal substrate [PN-EN 1607:2013] [kPa]	≥ 50
Adhesion of foam applied at 0°C to PVC substrate [PN-EN 1607:2013] [kPa]	≥ 50
Adhesion of foam applied at +30°C to the wood substrate [PN-EN 1607:2013] [kPa]	≥ 50
Adhesion of foam applied at +30°C to the metal substrate [PN-EN 1607:2013] [kPa]	≥ 50
Thermal resistance (after curing) [°C]	-40 - +90
Adhesion of foam applied at +30°C to PVC substrate [PN-EN 1607:2013] [kPa]	≥ 50
Colour	Value
Yellow	+
Conditions of application	Value
Can / applicator temperature (optimal +20°C) [°C]	+5 - +30
Ambient / surface temperature [°C]	-10 - +30

METHOD OF USE

Prior to application, read safety instruction presented at the end of TDS and in MSDS.

Surface preparation

- The foam presents adhesion to typical construction materials, such as: brick, concrete, plaster work, wood, metals, styrofoam, hard PVC and rigid PUR.
- The working surface should be cleaned and degreased.
- Sprinkle the working surface with water (with gardening sprinkler for example) at temperature >0°C.
- Secure surfaces exposed to accidental foam contamination.

Product preparation

- Too cold can should be brought to room temperature, e.g. by immersion in warm water with temperature up to 30°C or leaving it in room temperature for at least 24 h.

Application

- Put on protective gloves.

- Vigorously shake the can (10-20 seconds, the valve facing down) to thoroughly mix the components.
- Screw the can onto the applicator.
- Working position of the can is "valve facing down", however in case of a can at the temperature $>15^{\circ}\text{C}$ you can work with foam in any working position.
- Vertical gaps should be filled with foam starting at the bottom and moving up.
- Do not fill the entire gap – the foam will increase in volume.
- When sealing doors and windows, keep a minimum distance of 10 mm and a maximum of 30 mm between the opening framing and the door or window frame. Gaps > 30 mm are not recommended. Fill in gaps wider than 30 mm working bottom to top moving from one gap wall to another alternately, creating a zigzag pattern. Gaps > 50 mm are not permitted.
- Should application be interrupted for more than 5 minutes, the applicator nozzle with fresh foam should be cleaned with polyurethane foam cleaner and the can should be shaken prior to application.
- In case of foam drying in the applicator, the applicator tip with strainer at it's end should be cut off, which enables resuming work with foam as a standard.

Works after completion of application

- Immediately after full foam hardening, it should be secured against exposure to UV rays by using e.g. plaster or paints.

Remarks / restriction

- DOOR AND WINDOWS FITTING WITHOUT USING MECHANICAL COUPLING IS FORBIDDEN. LACK OF MECHANICAL COUPLINGS MAY CAUSE DEFORMATION OF THE MOUNTED ELEMENT.
- The curing process is dependent on temperature and humidity. The decrease in ambient temperature within 24 h after the application below the minimum application temperature can affect the quality and / or correctness of the seal.
- Hurried attempts at preliminary treatment may cause irreversible changes in foam structure and its stability and may affect deterioration of foam utility parameters.
- With the decrease of temperature decreases performance and increases the curing foam.
- The foam displays lack of adhesion to polyethylene, polypropylene, polyamide, silicone and Teflon.
- Fresh foam should be removed with polyurethane foam cleaner.
- Hardened foam may only be removed mechanically (e.g. with a knife).
- Quality and technical condition of used applicator affect the parameters of final product.
- The foam should not be used in spaces without access of fresh air and poorly ventilated or in places exposed to direct sunlight.
- Working in other position than "valve facing down" will decrease foam's efficiency.
- The manufacturer recommends using strip foam once (at one go), because in case of foam drying in the applicator, the future use may be impossible.
- Cutting off the strainer at the end of applicator will decrease foam's efficiency.

ADDITIONAL INFORMATION

The manufacturer recommends to commence finishing works after full hardening is completed, i.e. after 24 h.

All given parameters are based on laboratory tests compliant with internal manufacturer's standards and strongly depend on foam hardening conditions (ca, ambient, surface temperature, quality of used equipment and skills of person applying the foam).

Producer uses test methods approved by FEICA designed to deliver transparent and reproducible test results, ensuring customers have an accurate representation of product performance. FEICA OCF test methods are available at: <http://www.feica.com> (Our industry -> PU Foam (OCF) -> OCF Test Methods). FEICA is a multinational association representing the European adhesive and sealant industry, including one-component foam manufacturers.

TRANSPORT / STORAGE

The foam maintains its usability within 12 months from manufacturing date, provided that it is stored in original packaging in vertical position (valve facing up) in a dry place in temperature +5°C do +30°C . Storage in temperature exceeding +30°C shortens the shelf life of the product, adversely affecting its parameters. The product may be stored in temperature -5°C, no longer however than for 7 days (excluding transport). Storage of foam cans in temperature exceeding + 50°C or in vicinity of open flame is not allowed. Storage of the product in a position other than recommended may result in jamming the valve. The can cannot be squeezed or pierced even when it is empty.

Do not store the foam in the passenger compartment. Transported only in the trunk.

Detailed transport information is included in the Material Safety Data Sheet (MSDS).

Transport temperature	Foam transport period [days]
< -20°C	4
-19°C ÷ -10°C	7
-9°C ÷ -0°C	10

SAFETY AND HEALTH PRECAUTIONS

The information contained herein is offered in good faith based on Producer's research and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information shall not be used in substitution for customer's tests to ensure that Producer's products are fully satisfactory for your specific applications. Producer's sole warranty is that the product will meet its current sales specifications. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. Producer specifically disclaims any other expressed or implied warranty of fitness for a particular purpose or merchantability. Producer disclaims liability for any incidental or consequential damages. Suggestions of use shall not be taken as inducements to infringe any patent.