

TYTAN PROFESSIONAL SBS FIX Mounting Adhesive

One-component solvent-based adhesive based on styrene-butadiene rubber (SBS) for renovation and finishing works in the building industry. It has excellent adhesion to most substrates and increased joint strength.



BENEFITS

- fast and durable initial tack
- flexible joint
- high final strength
- excellent adhesion
- moisture resistant

RECOMMENDED USES

- for bonding of wide range of building materials to most typical surfaces, such as: concrete, plaster, chipboard, wood, plaster board, brick
- bonding of baseboards, plinths, doorsteps, floor panels, ceramic tiles
- bonding decorative elements made of wood, gypsum, cork, chipboard, metal, stones, foamed polystyrene
- bonding of mineral and glass wool
- clamping of carpets and PVC floor coverings

TECHNICAL DATA

Conditions of application	Value
Application temperature [°C]	+10 - +30
Optimal bonding temperature [°C]	+15 - +20
Optimal relative air humidity [%]	60
Uncured	Value
Base: synthetic rubber in organic solvents	+
Solid Content [%]	75 - 80
Density [g/cm ³]	1,20 - 1,30
Working time (depending on ambient conditions and subfloor properties) [min]	10 - 15
Consumption [g/m ²]	300 - 500
Full cure time [h]	72
Flammability	+
Cured	Value
Temperature resistance [°C]	-20 - +60
Flammability after curing	-
Colour	Value
Yellow	+

METHOD OF USE

Prior to application, read safety instruction presented in MSDS.

Surface preparation

- Bonded surfaces must be level, dry, free from contaminations and substances hindering adhesion.

Product preparation

- Cut the nozzle to the required diameter, cut the cartridge outlet and screw the nozzle. Insert the cartridge into the applicator gun.

Application

- Apply adhesive in spots or strips on the surface or bonded material.
- Immediately join the surfaces firmly together with a little twist motion, disconnect them, wait 3-5 minutes and press again strongly and evenly.
- Element's position can be easily corrected without disconnecting for 2-3 minutes after connection.

Works after completion of application

- Cleaning: before curing acetone or mineral spirits, after curing mechanically.
- DO NOT WASH HANDS WITH SOLVENTS.

Remarks / restriction

- Adhesion tests prior to application of the adhesive are recommended.
- Avoid contact with water until the adhesive is fully cured.
- Not recommended for PE, PP, Teflon, surfaces permanently wet.
- When bonding polystyrene elements – apply the adhesive economically, at long intervals, in thin strips, provide pressure and ventilation.
- Not recommended for thin polystyrene elements (during curing adhesive can lightly disturb the surface).
- Not suitable for solvent sensitive surfaces.

ADDITIONAL INFORMATION

All given parameters are based on laboratory tests compliant with internal manufacturer's standards and strongly depend on product hardening conditions (c.a., ambient, surface temperature, quality of used equipment and skills of person applying the product).

TRANSPORT / STORAGE

Warranted shelf life is 24 months from the manufacturing date when stored in unopened, original package at temperatures from +5 °C to +25 °C in a dry place protected from freezing and excessive heat.

CATALOGUE DATA

Nominal capacity / volume / size	Colour	Number of pieces per collective package	Index	EAN Code
290 ml	yellow	12	10045662	5902120178841

SAFETY AND HEALTH PRECAUTIONS

The product is inflammable. All works should be carried out in well-ventilated area away from ignition sources. Do not smoke. The adhesive should be stored in accordance with the rules of storage of inflammable substances. Detailed information is included in the Safety Data Sheet (SDS).

All written or oral information, recommendations and instructions are given according to our best knowledge, tests and experience, in good faith and in compliance with manufacturer's principles. Each user of this material will make sure in every possible way, including verification of the final product in proper conditions, about suitability of the supplied materials for their intended purposes. The manufacturer is not liable for any losses incurred due to inaccurate or erroneous application of the manufacturer's materials.