

TYTAN PROFESSIONAL Fire Block Extreme Insulating Foam Sealant 12



OZ

10051597

TYTAN Professional Fire Block Extreme Foam Sealant is a fire blocking foam sealant designed to work in the most extreme conditions, from -4°F to 100°F ambient temperatures. Though it is not approved as a fire stop, Fire Block Extreme is a certified draft blocking and fire blocking product. It is orange in color for easy inspection recognition. Fire Block Extreme uses a minimal shrinking technology to ensure an airtight seal while providing industry-leading yield. It offers minimal post-expansion for small gap filling while also being capable of filling gaps up to three inches. It offers premium adhesion to most construction materials including wood, metal, masonry, glass, vinyl, PVC, CPVC, plastics and more. For a Job Well Done, use TYTAN Professional Fire Block Extreme Insulating Foam Sealant!



ADVANTAGES

- Low foam flammability
- Made to perform in extreme temperature
- Orange color for easy identification
- Adheres to most construction materials
- Provides air and water resistant seal

RECOMMENDED USES

- Filling free spaces, cracks, gaps, pipe penetrations
- Sealing roof, wall and floor joints
- Sealing around electrical boxes and wiring
- Penetrations sealing around plumbing, HVAC and gas line penetrations

STANDARDS / APPROVALS / CERTIFICATES

Additional information

- NFPA 286

1/5

Update date: 18.03.2025

Selena USA, Inc.

4055 International Plaza, Suite 640, Fort Worth 76109,

e-mail: info@selenausa.com, www.tytan.com



- UL 723: Flame Spread 15, Smoke Development 10
- ASTM E84
- ICC-ES Report ESR-3302

TECHNICAL DATA

Parameter (73°F (+23°C)/50% RH)	Value
Nominal value [oz]	12
Capacity (free foaming) [cu.ft]	0,49 - 0,60
Capacity in gap (The value given for a gap with dimensions 35*1000*35 (width *length *depth [mm])) (RB024) [l]	11 - 13
Capacity in gap [cu.ft]	0,39 - 0,46
Secondary increase in volume (post-expansion) (EN 17333-2:2020) [%]	240 - 270
Skin formation time (EN 17333-3:2020) [min]	≤ 10
Cutting time (EN 17333-3:2020). The result given for a foam strip of 3 cm diameter. [min]	≤ 60
Full cure time (RB024) [h]	24
Heat conductivity coefficient (RB024) [W/mK]	≤ 0,036
Dimensional stability (EN 17333-2:2020) [%]	≤ 5
Flammability class (DIN 4102)	B3
Heat conductivity coefficient [BTU.in/hr.ft ² .°F]	≤ 0,25
Flame spread/Smoke developed (UL723 (ASTM E84))	15/10
Yield (linear yield of 1/2" width bead) [ft]	64
Application conditions	Value
Can/applicator temperature [°F] (optimum 68°F)	41 - 86
Ambient/substrate temperature [°F]	23 - 100
Color	Value
Orange	+

DIRECTIONS FOR USE

Prior to application, read safety instruction presented at the end of TDS and in MSDS.

Substrate preparation

- The foam presents ideal adhesion to typical construction materials, such as: brick, concrete, plaster work, wood, metals, styrofoam, hard PVC and rigid PUR.
- The working surface should be cleaned and degreased.
- Secure surfaces exposed to accidental foam contamination.

Product preparation

- If the can is too cold then the can should be brought to room temperature, e.g. by immersion in warm water with temperature up to 86°F (+30°C) or leaving it in room temperature for at least 24 h.
- Applicator temperature cannot be lower than can temperature.

Application

- Put on protective gloves.
- Vigorously shake the can (10-20 seconds, the valve facing down) to thoroughly mix the components.
- Screw the can onto the applicator.
- Working position of the can is “valve facing down”.
- Vertical gaps should be filled with foam starting at the bottom and moving up.
- Do not fill the entire gap – the foam will increase in volume.
- In case of sealing the open woodwork, gaps >1.18 in (3 cm) are not recommended. Gaps >1.97 in (5cm) are unacceptable. Slots wider than 1.18 in (3 cm) from the bottom to fill up from one wall to the other alternately forming a zigzag pattern.
- Should application be interrupted for more than 5 minutes, the applicator nozzle with fresh foam should be cleaned with polyurethane foam cleaner and the can should be shaken prior to application.

Post-application work

- Immediately after full foam hardening, it should be secured against exposure to UV rays by using e.g. plaster or paints.

Restrictions / notes

- The curing process is dependent on temperature and humidity. The decrease in ambient temperature within 24 h after the application below the minimum application temperature can affect the quality and / or correctness of the seal.
- Hurried attempts at preliminary treatment may cause irreversible changes in foam structure and its stability and may affect deterioration of foam utility parameters.
- Use opened foam packaging within 1 week
- The foam displays lack of adhesion to polyethylene, polypropylene, polyamide, silicone and Teflon.
- Fresh foam should be removed with polyurethane foam cleaner.
- Hardened foam may only be removed mechanically (e.g. with a knife).
- Quality and technical condition of used applicator affect the parameters of final product.
- The foam should not be used in spaces without access of fresh air and poorly ventilated or in places exposed to direct sunlight.

ADDITIONAL INFORMATION

All given parameters are based on laboratory tests compliant with internal manufacturer's standards and strongly depend on foam hardening conditions (ca, ambient, surface temperature, quality of used equipment and skills of person applying the foam).

The manufacturer recommends to commence finishing works after full hardening is completed, i.e. after 24 h.

Producer uses test methods approved by FEICA designed to deliver transparent and reproducible test results, ensuring customers have an accurate representation of product performance. FEICA OCF test methods are available at: <http://www.feica.com> (Our industry -> PU Foam (OCF) -> OCF Test Methods). FEICA is a multinational association representing the European adhesive and sealant industry, including one-component foam manufacturers.

TRANSPORT / STORAGE

The foam maintains its usability within 18 months from manufacturing date, provided that it is stored in original packaging in vertical position (valve facing up) in a dry place in temperature from 41°F (+5°C) to 86°F (+30°C). Storage in temperature exceeding 86°F (+30°C) shortens the shelf life of the product, adversely affecting its parameters. The product may be stored in temperature 23°F (-5°C), no longer than for 7 days (excluding transport). Storage of foam cans in temperature exceeding 122°F (+50°C) or in vicinity of open flame is not allowed. Storage of the product in a position other than recommended may result in jamming the valve. The can should not be squeezed or pierced even when it is empty. Do not store the foam in the passenger compartment. Transported only in the trunk.

Detailed transport information is included in the Material Safety Data Sheet (MSDS).

Transport temperature	Transport period [days]
< -4 °F (-20°C)	4
-2°F ÷ 14°F (-19°C ÷ -10°C)	7
16°F ÷ 32°F (-9°C ÷ 0°C)	10

CATALOG DATA

Nominal capacity / volume / size	Color	Pieces per pack	Index	EAN code
12 oz	N/A	12	10051597	820435037675

HEALTH AND SAFETY WARNINGS AND RECOMMENDATIONS

The information contained herein is offered in good faith based on Producer's research and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information shall not be used in substitution for customer's tests to ensure that Producer's products are fully satisfactory for your specific applications. Producer's sole warranty is that the product will meet its current sales specifications. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. Producer specifically disclaims any other expressed or implied warranty of fitness for a particular purpose or merchantability. Producer disclaims liability for any incidental or consequential damages. Suggestions of use shall not be taken as inducements to infringe any patent.