



10051564

When choosing the right window & door foam, you want a product that will expand to fill gaps with only one application, without melting, shrinking or bowing your windows. Window & Door Extreme is our most popular window & door foam for both residential and commercial construction. Designed to provide a wide range of application temperatures, as low as -4°, this low pressure, low expansion foam is ASTM E84 certified, and AAMA/FGIA verified to not bow windows.



#### **ADVANTAGES**

- May be used in temperatures -4°F 100°F (-20°C 38°C)
- Minimal shrinking; over-expanding
- Low pressure formula
- 20-50% more yield than competition

### RECOMMENDED USES

- Sealing for window fitting
- Filling gaps, cracks & penetrations
- Sealing roof, wall & floor joints

# STANDARDS / APPROVALS / CERTIFICATES

#### Additional information

- UL 723: Flame Spread 15, Smoke Development 10
- ASTM E84
- AAMA 812-19

**1/4** Update date: 11.03.2025



### **TECHNICAL DATA**

Parameter (73°F (+23°C)/50% RH)	Value		
Nominal value [oz]	24		
Skin formation time (EN 17333-3:2020) [min]	≤10		
Cutting time (EN 17333-3:2020). The result given for a foam strip of 3 cm diameter. [min]	≤ 40		
Full cure time (RB024) [h]	24		
R value	4 - 5		
Yield using 1/2" bead [ft]	1450		
Application conditions	Value		
Can/applicator temperature [°F] (optimum 68°F)	41 - 86		
Ambient/substrate temperature [°F]	-4 - 100		
Color	Value		
Yellow	+		

### **DIRECTIONS FOR USE**

Prior to application, read safety instruction presented in MSDS.

### **Substrate preparation**

- The foam presents ideal adhesion to typical construction materials, such as: brick, concrete, plaster work, wood, metals, styrofoam, hard PVC and rigid PUR.
- The working surface should be cleaned and degreased.
- Secure surfaces exposed to accidental foam contamination.

### **Product preparation**

- If the can is too cold then the can should be brought to room temperature, e.g. by immersion in warm water with temperature up to 86°F (+30°C) or leaving it in room temperature for at least 24 h.
- Applicator temperature cannot be lower than can temperature.

### **Application**

- Put on protective gloves.
- Vigorously shake the can (10-20 seconds, the valve facing down) to thoroughly mix the components.
- Screw the can onto the applicator.

2/4 Update date: 11.03.2025



- Working position of the can is "valve facing down".
- Vertical gaps should be filled with foam starting at the bottom and moving up.
- Do not fill the entire gap the foam will increase in volume.
- In case of sealing the open woodwork, gaps >1.18 in (3 cm) are not recommended. Gaps >1.97 in (5cm) are unacceptable. Slots wider than 1.18 in (3 cm) from the bottom to fill up from one wall to the other alternately forming a zigzag pattern.
- Should application be interrupted for more than 5 minutes, the applicator nozzle with fresh foam should be cleaned with polyurethane foam cleaner and the can should be shaken prior to application.

### **Post-application work**

- Immediately after full foam hardening, it should be secured against exposure to UV rays by using e.g. plaster or paints.
- After completion of work, the applicator should be thoroughly cleaned. To this end, a can with the cleaner should be screwed on the applicator and its trigger should be pushed until the moment, when clean fluid starts flowing out.

## **Restrictions / notes**

- DOOR AND WINDOWS FITTING WITHOUT USING MECHANICAL COUPLING IS FORBIDDEN. LACK OF MECHANICAL COUPLINGS MAY CAUSE DEFORMATION OF THE MOUNTED ELEMENT.
- The curing process is dependent on temperature and humidity. The decrease in ambient temperature within 24 h after the application below the minimum application temperature can affect the quality and / or correctness of the seal.
- Hurried attempts at preliminary treatment may cause irreversible changes in foam structure and its stability and may affect deterioration of foam utility parameters.
- Use opened foam packaging within 1 week
- The foam displays lack of adhesion to polyethylene, polypropylene, polyamide, silicone and Teflon.
- Fresh foam should be removed with polyurethane foam cleaner.
- Hardened foam may be removed mechanically (e.g. with a knife).
- Quality and technical condition of used applicator affect the parameters of final product.
- The foam should not be used in spaces without access of fresh air and poorly ventilated or in places exposed to direct sunlight.

### ADDITIONAL INFORMATION

All given parameters are based on laboratory tests compliant with internal manufacturer's standards and strongly depend on foam hardening conditions (ca, ambient, surface temperature, quality of used equipment and skills of person applying the foam).

The manufacturer recommends to commence finishing works after full hardening is completed, i.e. after 24 h.

Producer uses test methods approved by FEICA designed to deliver transparent and reproducible test results, ensuring customers have an accurate representation of product performance. FEICA OCF test methods are

3/4 Update date: 11.03.2025



available at: http://www.feica.com (Our industry -> PU Foam (OCF) -> OCF Test Methods). FEICA is a multinational association representing the European adhesive and sealant industry, including one-component foam manufacturers.

## TRANSPORT / STORAGE

The foam maintains its usability within 18 months from manufacturing date, provided that it is stored in original packaging in vertical position (valve facing up) in a dry place in temperature from 41°F (+5°C) to 86°F (+30°C). Storage in temperature exceeding 86°F (+30°C) shortens the shelf life of the product, adversely affecting its parameters. The product may be stored in temperature 23°F (-5°C), no longer than for 7 days (excluding transport). Storage of foam cans in temperature exceeding 122°F (+50°C) or in vicinity of open flame is not allowed. Storage of the product in a position other than recommended may result in jamming the valve. The can should not be squeezed or pierced even when it is empty. Do not store the foam in the passenger compartment. Transported only in the trunk.

Detailed transport information is included in the Material Safety Data Sheet (MSDS).

Transport temperature	Transport period [days]		
< -4°F (-20°C)	4		
-2°F ÷ 14°F (-19°C ÷ -10°C)	7		
16°F ÷ 32°F (-9°C ÷ -0°C)	10		

### **CATALOG DATA**

Nominal capacity / volume / size	Color	Pieces per pack	Index	EAN code
24 oz	N/A	12	10051564	820435037613

#### HEALTH AND SAFETY WARNINGS AND RECOMMENDATIONS

The information contained herein is offered in good faith based on Producer's research and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information shall not be used in substitution for customer's tests to ensure that Producer's products are fully satisfactory for your specific applications. Producer's sole warranty is that the product will meet its current sales specifications. Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted. Producer specifically disclaims any other expressed or implied warranty of fitness for a particular purpose or merchantability. Producer disclaims liability for any incidental or consequential damages. Suggestions of use shall not be taken as inducements to infringe any patent.

**4/4** Update date: 11.03.2025

